

BEST AVAILABLE COPY

<p>92-054171/07 L02 SHIK-17 04 90          SHIKOKU SOGO KENKYU (TAKJ)          17.04.90-JP-102233 (07.01.92) C04b-14/02 C04b-18/08 C04b-20          C04b-22/06 C04b-24 C04b-28/04          Cement compsn. for water-tight concrete - has amorphous silica          fines contg. discharged fly ash of specified size which is then          kneaded with aggregate and water          C92-024645</p>	<p>U/2-D13, 2-D14Q)</p>
<p>Full Patentees: Shikoku Sogo Kenkyu; Taisei Construction KK          Compsn is made by adding a suitable amt. of water reducing agent,          fly ash and amorphous silica fines in which the fly ash discharged on          firing coal is up to 20 microns in size. Resulting fly ash is then          kneaded with aggregate and water.          USE - Used for water-tight concrete for use at the underground          parts. (6pp Dwg.No.0/4)</p>	